



PCD HTC

1. PCD
2. PCD
3. PCD
4. VCT

PCD HTC

000	0000
000	0000 PCD
00000	1/2 PCD * 2T
000	PCD + HTC
000	000000
000	HTC EZ
000	00000000
000	HTC 000000
00000	000000000000

00000000000000000000000000
 00000000000000000000000000







Before Grinding and Polishing



After Grinding and Polishing

□□□

CONCRETE HARDNESS	Xtreme Hard	Very Hard	Hard	Medium Hard	Soft	Very Soft
PSI	6500–9000	5000–7000	4000–5000	3000–4000	1500–3500	1000–2000
MPA	C50–C65	C40–C55	C30–C50	C20–C40	C15–C25	C10–C20
CODE	XHF	VHF	HF	MHF	SF	VSF
COLOUR						

□□□□□□□□□□□□□□□□□□□□□□□□□□□□

□□□

□□□□□□□□□□□□□□□□□□□□□□□□□□□□

□□□

□□□□□□□□□□□□□□□□□□□□□□□□□□□□

□□□□□




Boreway Machinery Co., Ltd
www.diamondtools.top
www.boreway.net

2 PCD 3





Boreway Machinery Co., Ltd
www.diamondtools.top
www.boreway.net

PCD



Boreway Machinery Co., Ltd
www.diamondtools.top
www.boreway.net

PCD



1. 精密加工
2. OEM 加工
3. 检测
4. 仓储

5. 〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇

1. 〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇8〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

3. 〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇

1. 〇〇〇〇〇〇〇〇〇〇〇〇

2. 〇〇〇〇〇〇〇〇〇〇〇〇

3. 〇〇〇〇〇〇〇〇〇〇〇〇

〇〇〇〇〇

Fujian Nanan Boreway Machinery Co.,Ltd.

〇〇〇 〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇〇605

〇〇〇〇〇 362342

TEL 〇+86〇595-86990206 /〇+ 86〇 13559599186

〇〇〇 〇86〇595-86990220

〇〇〇〇〇 boreway05@boreway.net